

Nassimi LLC

Product Specification Sheet

team value

Pattern: Dakota

Date: 7/3/2008

Description

Weight (<i>linear yard</i>)	29.0 oz
Width	54 "
Thickness	0.90 mm
Gauge	0.036
Emboss	Special
Surface Composition	PVC/Rayon
Substrate Composition	Poly/Rayon Knit
Substrate Weight	3.8 oz

General Treatments

UV Resistance (CFFA-2 / ASTM G26-96 Method C)	40 Hours
Cold Crack (CFFA-6 Federal Standard No. 191A-Method 5874)	-10 F
Mildew Resistant (CFFA-120 / ASTM G21-96)	N/A
Anti-Bacterial / Anti-Microbial (CFFA-300 / AATCC* Test Method 147-1998)	N/A
Resilience SR	N/A
Bleach Resistant (diluted 1:10)	N/A

Physical Properties

Abrasion (CFFA-1A / Method ASTM D 4157-92)	30,000	Cycles
Adhesion (CFFA 3 / ASTM D751-98)	TBA	Warp
	TBA	Fill
Tear Strength (CFFA-16 / ASTM D2262)	5	Warp
	4.7	Fill
Tensile Strength and Elongation (CFFA-17 / ASTM D1682)	19.2	Warp
	10.9	Fill
Seam Strength (CFFA-14 / Method ASTM D751-98)	TBA	Warp
	TBA	Fill
Stretch and Set (CFFA-15 / SAE Method J-855)	TBA	Warp
	TBA	Fill

Flame Treatments

California Technical Bulletin 117	Pass
UFAC Class I	Pass
BIFMA CS-191-53, Section 3	Pass
BIFMA Upholstery, Section 4	Pass
MVSS 302	N/A
NFPA 260	N/A
Boston Fire Code (BFD IX-1)	N/A
IMO A.652(16)8.2	N/A
ASTM E84: Class I or A Rating	N/A

** CAL 133 (when used with suitable components)

*** Can be treated to pass FAR 25.853