

# Nassimi LLC

## Product Specification Sheet

**IMPERIAL Brand Fabrics**

**Pattern:** Imperial 630

**Date:** 12/17/2007

### Description

Weight ( <i>linear yard</i> )	18.5 oz
Width	58 "
Thickness	0.52 mm
Gauge	N/A
Emboss	Taffeta
Surface Composition	Polyester 600 x 300D
Substrate Composition	PVC
Thread Count	35T Warp 33T Weft

### General Treatments

UV Resistance ( <i>CFFA-2 / ASTM G26-96 Method C</i> )	N/A
Cold Crack ( <i>CFFA-6 Federal Standard No. 191A-Method 5874</i> )	-10 F
Mildew Resistant ( <i>CFFA-120 / ASTM G21-96</i> )	N/A
Anti-Bacterial / Anti-Microbial ( <i>CFFA-300 / AATCC* Test Method 147-1998</i> )	N/A
Resilience SR	N/A
Bleach Resistant (diluted 1:10)	N/A

### Physical Properties

Abrasion ( <i>CFFA-1A / Method ASTM D 4157-92</i> )	N/A	Cycles
Adhesion ( <i>CFFA 3 / ASTM D751-98</i> )	N/A	Warp Fill
Tear Strength ( <i>ASTM D 2261, Single Rip</i> )	N/A	Warp Fill
Tear Strength ( <i>ASTM D624</i> )	N/A	lbs/inch
Break Force ( <i>ASTM D 3597-02/D5034-95</i> )	184 136	Warp Fill
Pendulum Test Method ( <i>ASTM D 751, Section 22-28</i> )	N/A	Warp Fill

### Flame Treatments

California Technical Bulletin 117	Pass
UFAC Class I	Pass
BIFMA CS-191-53, Section 3	N/A
BIFMA Upholstery, Section 4	N/A
MVSS 302	N/A
NFPA 260	N/A
Boston Fire Code ( <i>BFD IX-1</i> )	N/A
IMO A.652(16)8.2	N/A
ASTM E84: Class I or A Rating	N/A

\*\* CAL 133 (*when used with suitable components*)

\*\*\* *Can be treated to pass FAR 25.853*