

Nassimi LLC

Product Specification Sheet

team value

Pattern: Primary Vinyls

Date: 10/8/2007

Description

Weight (<i>linear yard</i>)	24.0 oz
Width	54 "
Thickness	0.80 mm
Gauge	0.032
Emboss	Various
Surface Composition	PVC
Substrate Composition	Poly/Rayon Knit
Substrate Weight	3.5 oz

General Treatments

UV Resistance (CFFA-2 / ASTM G26-96 Method C)	200 Hours
Cold Crack (CFFA-6 Federal Standard No. 191A-Method 5874)	-10 F
Mildew Resistant (CFFA-120 / ASTM G21-96)	N/A
Anti-Bacterial / Anti-Microbial (CFFA-300 / AATCC* Test Method 147-1998)	N/A
Resilience SR	N/A
Bleach Resistant (diluted 1:10)	N/A

Physical Properties

Abrasion (CFFA-1A / Method ASTM D 4157-92)	30,000	Cycles
Adhesion (CFFA 3 / ASTM D751-98)		Warp Fill
Tear Strength (CFFA-16 / ASTM D5733-95)	13.6 20.8	Warp Fill
Tensile Strength and Elongation (CFFA-17 / ASTM D751-98)	82.9 68.7	Warp Fill
Seam Strength (CFFA-14 / Method ASTM D751-98)		Warp Fill
Stretch and Set (CFFA-15 / SAE Method J-855)		Warp Fill

Flame Treatments

California Technical Bulletin 117	Pass
UFAC Class I	Pass
BIFMA CS-191-53, Section 3	Pass
BIFMA Upholstery, Section 4	Pass
MVSS 302	N/A
NFPA 260	N/A
Boston Fire Code (BFD IX-1)	N/A
IMO A.652(16)8.2	N/A
ASTM E84: Class I or A Rating	N/A

** CAL 133 (when used with suitable components)

*** Can be treated to pass FAR 25.853