

Nassimi LLC

Product Specification Sheet

team value

Pattern: Promo Marine

Date: 6/3/2008

Description

Weight (<i>linear yard</i>)	28.0 oz
Width	54 "
Thickness	0.90 mm
Gauge	0.036
Emboss	Various
Surface Composition	PVC
Substrate Composition	Polyester
Substrate Weight	3.5 oz

General Treatments

UV Resistance <i>(CFFA-2 / ASTM G26-96 Method C)</i>	200 Hours
Cold Crack <i>(CFFA-6 Federal Standard No. 191A-Method 5874)</i>	-10 F
Mildew Resistant <i>(CFFA-120 / ASTM G21-96)</i>	N/A
Anti-Bacterial / Anti-Microbial <i>(CFFA-300 / AATCC* Test Method 147-1998)</i>	N/A
Resilience SR	N/A
Bleach Resistant (diluted 1:10)	N/A

Physical Properties

Abrasion <i>(CFFA-1A / Method ASTM D 4157-92)</i>	50,000	Cycles
Adhesion <i>(CFFA 3 / ASTM D751-98)</i>		Warp Fill
Tear Strength <i>(FTM 5136)</i>	21.4 21.65	Warp Fill
Break Strength <i>(FTM 5100.1)</i>	83.3 81.1	Warp Fill
Seam Strength <i>(CFFA-14 / Method ASTM D751-98)</i>		Warp Fill
Stretch and Set <i>(CFFA-15 / SAE Method J-855)</i>		Warp Fill

Flame Treatments

California Technical Bulletin 117	Pass
UFAC Class I	Pass
BIFMA CS-191-53, Section 3	Pass
BIFMA Upholstery, Section 4	Pass
MVSS 302	N/A
NFPA 260	N/A
Boston Fire Code <i>(BFD IX-1)</i>	N/A
IMO A.652(16)8.2	N/A
ASTM E84: Class I or A Rating	N/A

** CAL 133 (when used with suitable components)

*** Can be treated to pass FAR 25.853