

# Nassimi LLC

## Product Specification Sheet

**TEAMPERFORMANCE**

**Pattern:** Seaquest

**Date:** 6/3/2008

### Description

Weight ( <i>linear yard</i> )	32 oz
Width	54 "
Thickness	1 mm
Gauge	0.040
Emboss	Wallaby
Surface Composition	PVC
Substrate Composition	Poly/Rayon
Substrate Weight	3.75 oz

### General Treatments

UV Resistance (CFFA-2 / ASTM G26-96 Method C)	1,000 Hours
Cold Crack (CFFA-6 Federal Standard No. 191A-Method 5874)	-10 F
Mildew Resistant (CFFA-120 / ASTM G21-96)	Pass
Anti-Bacterial / Anti-Microbial (CFFA-300 / AATCC* Test Method 147-1998)	N/A
Resilience SR	N/A
Bleach Resistant (diluted 1:10)	N/A

### Physical Properties

Abrasion (CFFA-1A / Method ASTM D 4157-92)	70,000	Cycles
Adhesion (CFFA 3 / ASTM D751-98)		Warp Fill
Tear Strength (FTM 5136)	25.8 27.7	Warp Fill
Break Strength (FTM 5100.1)	89.2 102.7	Warp Fill
Seam Strength (CFFA-14 / Method ASTM D751-98)		Warp Fill
Stretch and Set (CFFA-15 / SAE Method J-855)		Warp Fill

### Flame Treatments

California Technical Bulletin 117	Pass
UFAC Class I	Pass
BIFMA CS-191-53, Section 3	Pass
BIFMA Upholstery, Section 4	Pass
MVSS 302	Pass
NFPA 260	N/A
Boston Fire Code (BFD IX-1)	N/A
IMO A.652(16)8.2	N/A
ASTM E84: Class I or A Rating	N/A

\*\* CAL 133 (when used with suitable components)

\*\*\* Can be treated to pass FAR 25.853