

Aura

DESCRIPTION

WEIGHT (LINEAR YARD)	18.0oz
WIDTH	54"
THICKNESS	0.80mm
EMBOSS	Paper
SURFACE COMPOSITION	100% Polyurethane
SUBSTRATE COMPOSITION	100% Polyester Knit

GENERAL TREATMENTS

HYDROLYSIS RESISTANCE	7 weeks , ISO1419:1995 (Jungle Test)
COLORFASTNESS TO LIGHT	200 Hours, CFFA-2 / AATCC 16-3
COLD CRACK	-20° F, CFFA-6a Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass, CFFA-120 / ASTM G21-96
ANTI-BACTERIAL / ANTI-MICROBIAL	Pass, CFFA-300 / AATCC* Test Method 147-1998
STAIN RESISTANT	Yes, with Cleangene™ Technology
BLEACH RESISTANT	Yes, 3:1 Dilution

PHYSICAL PROPERTIES

ABRASION	500,000 Double Rubs, CFFA-1A / Method ASTM D4157-92
COATING ADHESION	10.3 Warp, 10.37 Fill, CFFA 3 / ASTM D751-98
TEAR STRENGTH: TONGUE TEAR	10.3 Warp, 16.2 Fill, CFFA 16b / CFFA-16b / ASTM D2261-96
BREAKING STRENGTH	172 Warp, 103 Fill, CFFA-17 / ASTM D751-10
SEAM STRENGTH: TACK TEAR	63.4 Warp, 46.3 Fill, CFFA-14 / Method ASTM D751-07
BLOCKING RESISTANCE	2 Rating, CFFA-4 / FTMS 191A-Method 5872
CROCKING	4.5 Dry, 4.5 Wet, AATCC-Method 8-2001

FLAME TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS 1	Pass
NFPA 260	Pass
IMO 2010 FTP CODE, PART 8 (3.1)	Pass
ASTM E-84 (ADHERED & UNADHERED): CLASS 1 OR A	Pass