

## Aura

### DESCRIPTION

|                       |                     |
|-----------------------|---------------------|
| WEIGHT (LINEAR YARD)  | 18.0oz              |
| WIDTH                 | 54"                 |
| THICKNESS             | 0.80mm              |
| EMBOSS                | Paper               |
| SURFACE COMPOSITION   | 100% Polyurethane   |
| SUBSTRATE COMPOSITION | 100% Polyester Knit |

### GENERAL TREATMENTS

|                                 |                                                       |
|---------------------------------|-------------------------------------------------------|
| HYDROLYSIS RESISTANCE           | 7 weeks , ISO1419:1995 (Jungle Test)                  |
| COLORFASTNESS TO LIGHT          | 200 Hours, CFFA-2 / AATCC 16-3                        |
| COLD CRACK                      | -20° F, CFFA-6a Federal Standard No. 191A-Method 5874 |
| MILDEW RESISTANT                | Pass, CFFA-120 / ASTM G21-96                          |
| ANTI-BACTERIAL / ANTI-MICROBIAL | Pass, CFFA-300 / AATCC* Test Method 147-1998          |
| STAIN RESISTANT                 | Yes, with Cleangene™ Technology                       |
| BLEACH RESISTANT                | Yes, 3:1 Dilution                                     |

### PHYSICAL PROPERTIES

|                            |                                                           |
|----------------------------|-----------------------------------------------------------|
| ABRASION                   | 500,000 Double Rubs, CFFA-1A / Method ASTM D4157-92       |
| COATING ADHESION           | 10.3 Warp, 10.37 Fill, CFFA 3 / ASTM D751-98              |
| TEAR STRENGTH: TONGUE TEAR | 10.3 Warp, 16.2 Fill, CFFA 16b / CFFA-16b / ASTM D2261-96 |
| BREAKING STRENGTH          | 172 Warp, 103 Fill, CFFA-17 / ASTM D751-10                |
| SEAM STRENGTH: TACK TEAR   | 63.4 Warp, 46.3 Fill, CFFA-14 / Method ASTM D751-07       |
| BLOCKING RESISTANCE        | 2 Rating, CFFA-4 / FTMS 191A-Method 5872                  |
| CROCKING                   | 4.5 Dry, 4.5 Wet, AATCC-Method 8-2001                     |

### FLAME TREATMENTS

|                                               |      |
|-----------------------------------------------|------|
| CALIFORNIA TECHNICAL BULLETIN 117:13          | Pass |
| UFAC CLASS 1                                  | Pass |
| BIFMA CS-191-53, SECTION 3&4                  | Pass |
| NFPA 260                                      | Pass |
| IMO 2010 FTP CODE, PART 8 (3.1)               | Pass |
| ASTM E-84 (ADHERED & UNADHERED): CLASS 1 OR A | Pass |