

## Beckett

### DESCRIPTION

WEIGHT (LINEAR YARD)	20.0oz
WIDTH	54"
THICKNESS	1.00mm
GAUGE	0.04
SURFACE COMPOSITION	100% Polyurethane (Polycarbonate)
SUBSTRATE COMPOSITION	100% Polyester

### GENERAL TREATMENTS

HYDROLYSIS RESISTANCE	7 weeks , ISO 1419:1995 (Jungle Test)
COLORFASTNESS TO LIGHT	200 Hours, AATCC 16.3-2014, Option 3
COLD CRACK	-20° F, CFFA-6a Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass,CFFA-120/ ASTM G21-96
ANTI-BACTERIAL	Pass, AATCC 147-2011
ANTI-MICROBIAL	Pass, ASTM G21-13
STAIN RESISTANT	Yes, with Writer's Block™
BLEACH RESISTANT	Yes, 20% Dilution

### PHYSICAL PROPERTIES

ABRASION	150,000+ Double Rubs ASTM D4157-13 Act Standard Cottonduck
COATING ADHESION	11.4 Warp, 10.8 Fill, ASTM D751-06
TEAR STRENGTH: TONGUE TEAR	5.1 Warp, 2.9 Fill, ASTM D751-06
BREAKING STRENGTH	144 Warp, 113 Fill, ASTM D751-06
SEAM STRENGTH:TACK TEAR	59.6 Warp, 44.4 Fill, Method ASTM D751-06
CROCKING	5 Dry, 5 Wet AATCC 8-2016

### FLAME TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS 1	Pass
FMVSS 302	Pass
NFPA 260	Pass
ASTM E- 84 (UNADHERED) : CLASS 1 OR A	Pass

### REDUCED ENVIRONMENTAL IMPACT

- PHthalate FREE (INCLUDES ALL PHthalATES LISTED IN CAL PROP 65 & CPSIA)
- LEAD FREE
- BPA FREE/TRIS FREE/FORMALDEHYDE FREE
- DOES NOT CONTAIN CONFLICT MINERALS



\*ACT® Registered Certification Marks