

Bondi

DESCRIPTION

WEIGHT (LINEAR YARD)	32 oz
WIDTH	54"
THICKNESS	1.0 mm
SURFACE COMPOSITION	PVC
SUBSTRATE COMPOSITION	100% Polyester
SUBSTRATE WEIGHT	3.75 oz

GENERAL TREATMENTS

UV RESISTANCE	1,000 Hours, CFFA-2 / ASTM G26-96 Method C
COLD CRACK	-20° F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass, CFFA-120 / ASTM G21-96

PHYSICAL PROPERTIES

ABRASION	300,000+ Cycle, CFFA-1A / Method ASTM D 4157-07
TEAR STRENGTH: TONGUE TEAR	25.8 Warp, 28 Fill, CFFA-16 / Method ASTM D 2261
BREAKING STRENGTH	89.2 Warp, 103 Fill, CFFA-17 / Method ASTM D 751-06

FLAME TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS 1	Pass
BIFMA CS-191-53, SECTION 3	Pass
BIFMA UPHOLSTERY, SECTION 4	Pass
MVSS 302	Pass
NFPA 260	Pass
IMO 2010 FTP CODE, PART 8	Pass