

## Bottega

### GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	28.0 oz
WIDTH	54"
THICKNESS	1.00mm
GAUGE	0.040
SURFACE COMPOSITION	PVC 60%
SUBSTRATE COMPOSITION	Polyester 40%
SUBSTRATE WEIGHT	4.0 oz

### GENERAL TREATMENTS

UV RESISTANCE	300 Hours, CFFA-2 / ASTM G26-96 Method C
COLD CRACK	-20° F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass, CFFA-120 / ASTM G21-96
ANTI-BACTERIAL	Pass, CFFA-300 / AATCC* Test Method 147-1998
ANTI-MICROBIAL	Pass, CFFA-300 / AATCC* Test Method 147-1998
STAIN RESISTANT	Yes, with Resilience <sup>SR</sup>
BLEACH RESISTANT	Yes, 1:10 Dilution

### PHYSICAL STRENGTH PROPERTIES

ABRASION	300,000+ Cycles, CFFA-1A/ Method ASTM D 4157-92
COATING ADHESION	13.3 Warp, 12.11 Fill, CFFA 3/ ASTM D751-98
TEAR STRENGTH: TONGUE TEAR	6.7 Warp, 8.5 Fill, CFFA-16/ ASTM D5733-95
BREAKING STRENGTH	93 Warp, 67 Fill, CFFA-17/ ASTM D751-98
SEAM STRENGTH: TACK TEAR	45.2 Warp, 34.3 Fill, CFFA-14/ Method ASTM D751-98
BLOCKING RESISTANCE	2 Rating, CFFA-4/ FTMS 191A-TM5872
CROCKING	4.5 Dry, 4.5 Wet, AATCC-Method 8-2001
FLEX TESTING OF FINISH	25,000 Warp, 25,000 Fill, CFFA-10/ASTM D2097-03(2005)

### FLAME RETARDANCY STANDARDS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS 1	Pass
BIFMA CS-191-53, SECTION 3	Pass
BIFMA UPHOLSTERY, SECTION 4	Pass
NFPA 260	Pass
BOSTON FIRE CODE(BFD IX-1)	Pass
MVSS 302	Pass
IMO 2010 FTP CODE, PART8	Pass
ASTM E- 84 (ADHERED & UNADHERED): CLASS I OR A	Pass