

## Classic

### DESCRIPTION

WEIGHT (LINEAR YARD)	29.0 oz
WIDTH	54"
THICKNESS	1.20 mm
GAUGE	0.048
SURFACE COMPOSITION	100% PVC (Phthalate Free)
SUBSTRATE COMPOSITION	100% Brushed Polyester Knit
SUBSTRATE WEIGHT	4.4 oz

### GENERAL TREATMENTS

COLORFASTNESS TO LIGHT	1000 Hours ASTM G154-12a & AATCC Test Method 16-2004, Option 3
COLD CRACK	-20 °F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass, CFFA-120 / ASTM G21-09
ANTI-BACTERIAL	Pass, CFFA-300 / AATCC* Test Method 147-2011
ANTI-MICROBIAL	Pass, CFFA-120 / ASTM G21-09
STAIN RESISTANT	Yes, with Resilience™
BLEACH RESISTANT	Yes, 10% Dilution

### PHYSICAL STRENGTH PROPERTIES

ABRASION	500,000+ Double Rubs, CFFA-1A / Method ASTM D 4157-10 ACT STANDARD COTTONDUCK
TEAR STRENGTH: TONGUE TEAR	6.2 Warp, 7.9 Fill, CFFA-16/ASTM D751-06
BREAKING STRENGTH	115 Warp, 102 Fill, CFFA-17 / ASTM D751-06
SEAM STRENGTH: TACK TEAR	53.3 Warp, 49.6 Fill, CFFA-14 / Method ASTM D751-06
CROCKING	5 Dry, 5 Wet, AATCC-Method 8-2016
FLEX TESTING OF FINISH	25,000 Warp, 25,000 Fill, CFFA-10/ASTM D2097-03(2010)
COATING ADHESION	5 Warp, 4.9 Fill, ASTM D751-06

### FLAME TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117, SECTION E	Pass
UFAC CLASS 1	Pass
MVSS 302	Pass
NFPA 260	Pass
IMO 2010 FTP CODE, PART 8	Pass
ASTM E-84 (ADHERED & UNADHERED): CLASS 1 OR A	Pass



\*ACT® Registered Certification Marks