

Cork

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	18.0 oz
WIDTH	54"
THICKNESS	0.80 mm
EMBOSS	Paper
SURFACE COMPOSITION	100% Polyurethane (Polycarbonate)
SUBSTRATE COMPOSITION	100% Polyester

GENERAL TREATMENTS

HYDROLYSIS RESISTANCE	7 weeks, ISO 1419:1995 (Jungle Test)
COLOR FASTNESS TO LIGHT	200 Hours/ AATCC16:3-2014, Option 3
COLD CRACK	-20°F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass, CFFA-120 / ASTM G21-96
ANTI-BACTERIAL/ ANTI-MICROBIAL	Pass, CFFA-300 / AATCC* Test Method 147-1998
STAIN RESISTANT	Yes, with Cleangene™ technology
BLEACH RESISTANT	Yes, 10% Dilution AATCC107-2013

PHYSICAL STRENGTH PROPERTIES

ABRASION	150,000+ Double Rubs, CFFA-1A/ Method ASTM D 4157-92
COATING ADHESION	7.92 Warp, 7.77 Fill, CFFA 3/ ASTM D751-06
TEAR STRENGTH: TONGUE TEAR	9.5 Warp, 13.4 Fill, CFFA-16/ ASTM D2261-96
BREAKING STRENGTH	143 Warp, 68 Fill, CFFA-17/ ASTM D751-06
SEAM STRENGTH: TACK TEAR	56 Warp, 38.2 Fill, CFFA-14/ Method ASTM D751-06
BLOCKING RESISTANCE	1 Rating, CFFA-4/FTMS 191A-TM5872
CROCKING	5 Dry, 5Wet, AATCC-Method 8-2001

FLAME TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS 1	Pass
NFPA 260	Pass
IMO 2010 FTP CODE, PART 8 (3.1)	Pass
ASTM E-84 (ADHERED & UNADHERED): CLASS 1 OR A	Pass
FMVSS 302	Pass

REDUCED ENVIRONMENTAL IMPACT

- 21P PHTHALATE FREE (INCLUDES ALL PHTHALATES LISTED IN CAL PROP 65 & CPSIA)
- LEAD FREE
- BPA FREE/TRIS FREE/FORMALDEHYDE FREE
- DOES NOT CONTAIN CONFLICT MINERALS
- PVC FREE
- HEAVY METAL FREE
- 99% OF ALL WATER AND RAW MATERIALS USED IN PRODUCTION ARE RECLAIMED AND RECYCLED
- WATER AND ENERGY EFFICIENT PRODUCTION



*ACT® Registered Certification Marks