

NASSIMI

PRODUCT SPECIFICATION SHEET

Harrison Wool

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD) 15-16 oz
WIDTH 54"

PIECE DYED YARN DYED FIBER DYED
 DOBBY JACQUARD PILE

YARN PER INCH 38.1 EPI, 34.5 PPI
YARN SIZE MN 8.3 Warp, MN 8.3 Fill
MINIMUM YARDAGE CUSTOM COLOR 400 Yards
COMPOSITION 70% Wool, 20% Polyester, 5% Acrylic, 5% Nylon
CLEANING CODE SW, Spot clean with upholstery shampoo, foam from a mild detergent, or mild dry cleaning solvent. Do not saturate with liquid. Pile fabrics may require brushing to restore appearance. Cushion covers should not be removed and dry cleaned.

PHYSICAL PROPERTIES

ABRASION 75,000+ Cycles, Martindale, Martindale Method ASTM D 4966-12
BREAKING STRENGTH 108.3 Warp, 57.4 Fill, Method ASTM 5034
BRUSH PILL Class 3.0, ASTM D3511
SEAM SPILLAGE 86.9 Warp, 56.0 Fill, Method ASTM D4034-92
TEAR STRENGTH: TONGUE TEAR 11.8 Warp, 7.0 Fill, ASTM D2261-13
CROCKING 5 Dry, 5.0 Wet, AATCC-8
COLORFASTNESS TO LIGHT Class 5.0, 40 Hours, AATCC16 Option 3

FLAME RETARDANCY

CALIFORNIA TECHNICAL BULLETIN 117:13 Pass
NFPA 260 Pass
UFAC CLASS I Pass

TARIFF CODE 5111.30.0500



*ACT® Registered Certification Marks