

Imperial 600

DESCRIPTION

WEIGHT (LINEAR YARD)	24.0 oz
WIDTH	58"
THICKNESS	0.62 mm
EMBOSS	Taffeta
SURFACE COMPOSITION	100% Polyester
SUBSTRATE COMPOSITION	PVC 600 x 300D
SUBSTRATE THREAD COUNT	35 x 33

GENERAL TREATMENTS

COLD CRACK	-10 F, CFFA-6 Federal Standard No. 191A-Method 5874
------------	---

PHYSICAL PROPERTIES

ABRASION	1000 Cycles, CFFA-1B/ Method ASTM D 3884-01
TEAR STRENGTH	12.7 Warp, 24.4 Fill, ASTM D2261-07
BREAKING STRENGTH	314.1 Warp, 372.2 Fill, FTM 5100.1
FLEX RESISTANCE OF FINISH	25,000 Warp, 25,000 Fill, CFFA-10/ ASTM D2097-3(2005)

FLAME TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
--------------------------------------	------