

Impression

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	31 oz
WIDTH	54"
THICKNESS	1.20 mm
GAUGE	0.048
SURFACE COMPOSITION	100% Phthalate Free PVC
SUBSTRATE COMPOSITION	100% Polyester

GENERAL TREATMENTS

COLORFASTNESS TO LIGHT	200 Hours, ASTM G154-06 & AATCC Test Method 16-2004, Option 3
COLD CRACK	-20 °F, CFFA-6 Federal Standard No. 191A-Method 5874
STAIN RESISTANT	Yes, with RESILIENCE ^{SR}
BLEACH RESISTANT	Yes, 10% Dilution

PHYSICAL STRENGTH PROPERTIES

ABRASION	250,000, Double Rubs, CFFA-1A / Method ASTM D 4157-10 ACT STANDARD COTTONDUCK
PRINT RETENTION	250 Cycles, ASTM D3389-15
TEAR STRENGTH: TONGUE TEAR	8.0 Warp, 6.6 Fill, CFFA-16 / ASTM D2261-07a
BREAK STRENGTH	106 Warp, 92 Fill, CFFA-17 / ASTM D751-06
SEAM STRENGTH: TACK TEAR	58.3 Warp, 45.9 Fill, CFFA-14 / Method ASTM D751-06
CROCKING	5.0 Dry, 5.0 Wet, AATCC-Method 8-2007
COATING ADHESION	7.8 Warp, 7.6 Fill, ASTM D751-06

FLAME RETARDANCY STANDARDS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS 1	Pass
MVSS 302	Pass
NFPA 260	Pass
IMO 2010 FTP CODE, PART 8	Pass

REDUCED ENVIRONMENTAL IMPACT

Phthalate Free (includes all Phthalates listed in CAL Prop 65 & CPSIA)
Lead Free
BPA Free/TRIS Free/Formaldehyde Free
Does not contain Conflict Minerals