

## Jive

### GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	18.0 oz
WIDTH	54"
THICKNESS	0.80 mm
EMBOSS	Paper
SURFACE COMPOSITION	100 % Polyurethane (Polycarbonate)
SUBSTRATE COMPOSITION	100 % Polyester

### GENERAL TREATMENTS

HYDROLYSIS RESISTANCE	7 weeks, ISO1419:1995 (Jungle Test)
COLORFASTNESS TO LIGHT	200 Hours, CFFA-2 / AATCC 16-3
COLD CRACK	-20 °F, CFFA-6a Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass, CFFA-120 / ASTM G21-96
ANTI-BACTERIAL / ANTI-MICROBIAL	Pass, CFFA-300 / AATCC* Test Method 147-1998
STAIN RESISTANT	Yes, with Cleangene™ Technology
BLEACH RESISTANT	Yes, 10% Dilution, AATCC 107-2013

### PHYSICAL STRENGTH PROPERTIES

ABRASION	500,000 Double Rubs, CFFA-1A / Method ASTM D 4157-92
COATING ADHESION	7.7 Warp, 9.8 Fill, CFFA 3 / ASTM D751-06
TEAR STRENGTH: TONGUE TEAR	11.11 Warp, 15.9 Fill, CFFA-16b / ASTM D2261-96
BREAKING STRENGTH	123 Warp, 65 Fill, CFFA-17 / ASTM D751-06
SEAM STRENGTH: TACK TEAR	58.7 Warp, 40.6 Fill, CFFA-14 / Method ASTM D751-06
BLOCKING RESISTANCE	2 Rating, CFFA-4 / FTMS 191A-Method 5872
CROCKING	4.5 Dry, 4.5 Wet, AATCC-Method 8-2001

### FLAME RETARDANCY

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass
IMO 2010 FTP CODE, PART 8 (3.1)	Pass
ASTM E-84 (ADHERED & UNADHERED): CLASS 1 OR A	Pass

### REDUCED ENVIRONMENTAL IMPACT

PHthalate FREE (INCLUDES ALL PHthalATES LISTED IN CAL PROP 65 & CPSIA)

LEAD FREE

BPA FREE/TRIS FREE/FORMALDEHYDE FREE

DOES NOT CONTAIN CONFLICT MINERALS

PVC FREE

HEAVY METAL FREE

99% OF ALL WATER AND RAW MATERIALS USED IN PRODUCTION ARE RECLAIMED AND RECYCLED

WATER & ENERGY EFFICIENT PRODUCTION



\*ACT® Registered Certification Marks