

Kosta

DESCRIPTIONS

WEIGHT (LINEAR YARD)	18.0 OZ
WIDTH	54"
THICKNESS	0.80 mm
EMBOSS	Paper
SURFACE COMPOSITION	100 % Polyurethane
SUBSTRATE COMPOSITION	100 % Polyester Knit

GENERAL TREATMENTS

HYDROLYSIS RESISTANCE	7 weeks, ISO1419:1995 (Jungle Test)
COLORFASTNESS TO LIGHT	200 Hours, CFFA-2 / AATCC 16-3
COLD CRACK	-20 °F, CFFA-6a Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass, CFFA-120 / ASTM G21-96
ANTI-BACTERIAL / ANTI-MICROBIAL	Pass, CFFA-300 / CFFA-300/ AATCC*Test Method 147-1998
STAIN RESISTANT	Yes, with Cleangene™ Technology
BLEACH RESISTANT	Yes, 3:1 Dilution

PHYSICAL PROPERTIES

ABRASION	100,000 Double Rubs, CFFA-1A / Method ASTM D 4157-92
COATING ADHESION	10.15 Warp, 13.4 Fill, CFFA 3 / ASTM D751-06
TEAR STRENGTH: TONGUE TEAR	9.5 Warp, 13.4 Fill, CFFA-16b / ASTM D2261-96
BREAKING STRENGTH	146 Warp, 75 Fill, CFFA-17 / ASTM D751-06
SEAM STRENGTH: TACK TEAR	56.5 Warp, 40.7 Fill, CFFA-14 / Method ASTM D751-06
BLOCKING RESISTANCE	3 Rating, CFFA-4 / FTMS 191A-Method 5872
CROCKING	5 Dry, 4.5 Wet, AATCC-Method 8-2001

FLAME RETARDANCY

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass
IMO 2010 FTP CODE, PART8 (3.1)	Pass
ASTM E-84 (ADHERED & UNADHERED): CLASS 1 OR A	Pass

REDUCED ENVIRONMENTAL IMPACT

- PHthalate FREE (INCLUDES ALL PHthalATES LISTED IN CAL PROP 65 & CPSIA)
- LEAD FREE
- BPA FREE/TRIS FREE/FORMALDEHYDE FREE
- DOES NOT CONTAIN CONFLICT MINERALS



*ACT® Registered Certification Marks