

LEATHERTEX

DESCRIPTION

WEIGHT (LINEAR YARD)	67.0 oz
WIDTH	54"
THICKNESS	3.00 mm
GAUGE	0.116 mm
EMBOSS	Wallaby
SURFACE COMPOSITION	PVC
SUBSTRATE COMPOSITION	Polyester
SUBSTRATE WEIGHT	7.7 oz

GENERAL TREATMENTS

UV RESISTANCE	200 HOURS, (CFFA-2 / ASTM G26-96 METHOD C)
COLD CRACK	-20 F, (CFFA-6 Federal Standard No. 191A-Method 5874)
MILDEW RESISTANT	YES (CFFA-120 / ASTM G21-96)
ANTI-BACTERIAL / ANTI-MICROBIAL	N/A (CFFA-300 / AATCC* Test Method 147-1998)
RESILIENCE SR	N/A
BLEACH RESISTANT (DILUTED 1:10)	N/A

PHYSICAL PROPERTIES

ABRASION	50,000 CYCLES, CFFA - 1A / METHOD ASTM D 4157-92
ADHESION	N/A WARP, NA/ FILL, (CFFA-16 / ASTM D5733-95)
TEAR STRENGTH	6.6 Warp, 6.6 Fill (CFFA-16 / ASTM D5733-95)
TENSILE STRENGTH AND ELONGATION	77.0 Warp, 77.0 Fill (CFFA-17 / ASTM D751-98)
SEAM STRENGTH	N/A Warp, N/A Fill (CFFA-14 / Method ASTM D751-98)
STRETCH AND SET	N/A Warp, N/A Fill (CFFA-15 / SAE Method J-855)

FLAME TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117	Pass
UFAC CLASS 1	Pass
BIFMA CS-191-53, SECTION 3	Pass
BIFMA UPHOLSTERY, SECTION 4	Pass
MVSS 302	Pass
NFPA 260	N/A
BOSTON FIRE CODE (BFD IX-1)	N/A
IMO A.652(16)8.2	N/A
ASTM E84: Class I or A Rating	N/A