

Madison

DESCRIPTIONS

WEIGHT (LINEAR YARD)	38.0 oz
WIDTH	54"
THICKNESS	1.30 mm
GAUGE	0.052
EMBOSS	SE 757
SURFACE COMPOSITION	PVC
SUBSTRATE COMPOSITION	Poly 75/ Cotton 25
SUBSTRATE WEIGHT	N/A

GENERAL TREATMENTS

UV RESISTANCE	200 Hours, CFFA-2/ ASTM G26-96 Method C
COLD CRACK	-20 F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	N/A, CFFA-120 / ASTM G21-96
ANTI-BACTERIAL	N/A, CFFA-300 / AATCC* Test Method 147-2004
ANTI-MICROBIAL	N/A, CFFA-300 / AATCC* Test Method 147-2004
STAIN RESISTANCE	N/A
BLEACH RESISTANT	N/A

PHYSICAL PROPERTIES

ABRASION	100,000 Cycles, CFFA-1A/ Method ASTM D 4157-92
ADHESION	N/A, 13.4 Fill, CFFA 3/ ASTM D751-98
TEAR STRENGTH	5.8 Warp, 5.8 Fill, CFFA-16/ ASTM D5733-95
TENSILE STRENGTH AND ELONGATION	54 Warp, 72 Fill, CFFA-17/ ASTM D751-98
SEAM STRENGTH	59 Warp, 56.5 Fill, CFFA-14/ Method ASTM D751-98
BLOCKING RESISTANCE	2 Rating, CFFA-4/ FTMS 191A-TM5872
CROCKING	4 Dry, 4.5 Wet, AATCC-Method 8-2001
FLEX TESTING OF FINISH	25,000 Warp, 25,000 Fill, CFFA-10/ASTM D2097-03(2005)

FLAME RETARDANCY

CALIFORNIA TECHNICAL BULLETIN 117	Pass
UFAC CLASS I	Pass
BIFMA CS-191-53, SECTION 3	Pass
BIFMA UPHOLSTERY, SECTION 4	Pass
MVSS 302	Pass
NFPA 206	Pass
BOSTON FIRE CODE (BFD IX-1)	N/A
IMO A.652(16)8.2	Pass
IMO A.652(16)8.2	Pass
ASTM E 84: CLASS I OR A RATING	Pass