

New Soho

DESCRIPTION

WEIGHT (LINEAR YARD)	28.0 oz
WIDTH	54"
THICKNESS	0.90 mm
GAUGE	0.036
EMBOSS	New Soho
SURFACE COMPOSITION	PVC
SUBSTRATE COMPOSITION	Polyester Knit
SUBSTRATE WEIGHT	3.5 oz

GENERAL TREATMENTS

UV RESISTANCE	200 hours, CFFA-2/ ASTM G26-96 Method C
COLD CRACK	-10 F, CFFA-6 Federal Standard No. 191A-Method 5874

PHYSICAL STRENGTH PROPERTIES

ABRASION	50,000 Cycles, CFFA-1A/ Method ASTM D 4157-92
TEAR STRENGTH: TONGUE TEAR	13.1 Warp, 10.8 Fill, CFFA-16/ ASTM D5733-95
BREAKING STRENGTH	77.6 Warp, 75.1 Fill, CFFA-17/ ASTM D751-98

FLAME RETARDANCY

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS 1	Pass
BIFMA CS-191-53, SECTION 3	Pass
BIFMA UPHOLSTERY, SECTION 4	Pass