

Olympia

DESCRIPTION

WEIGHT (LINEAR YARD)	28.0 oz
WIDTH	54"
THICKNESS	0.90 mm
GAUGE	0.036
SURFACE COMPOSITION	PVC
SUBSTRATE COMPOSITION	Polyester Knit
SUBSTRATE WEIGHT	3.5 oz

GENERAL TREATMENTS

UV RESISTANCE	200 hours, CFFA-2/ ASTM G26-96 Method C
COLD CRACK	-10 F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	N/A, CFFA-120/ AATCC G21-96
ANTI-BACTERIAL	N/A, CFFA-300/ AATCC* Test Method 147-1998
ANTI-MICROBIAL	N/A, CFFA-300/ AATCC* Test Method 147-1998
RESILIENCE FSR	N/A
BLEACH RESISTANT	N/A

PHYSICAL STRENGTH PROPERTIES

ABRASION	30,000 Cycles, CFFA-1A/ Method ASTM D 4157-92
ADHESION	N/A Warp, N/A Fill, CFFA 3/ ASTM D751-98
TEAR STRENGTH	14.4 Warp, 22,7 Fill, CFFA-16/ ASTM D5733-95
TENSILE STRENGTH & ELONGATION	62 Warp, 68 Fill, CFFA-17/ ASTM D751-98
SEAM STRENGTH	N/A Warp, N/A Fill, Method ASTM D751-98
STRETCH & SET	CFFA-15/ SAE Method J-855

FLAME RETARDANCY

CALIFORNIA TECHNICAL BULLETIN 117	Pass
UFAC CLASS 1	Pass
BIFMA CS-191-53, SECTION 3	Pass
BIFMA UPHOLSTERY, SECTION 4	Pass
MVSS 302	N/A
NFPA 260	N/A
BOSTON FIRE CODE (BFD IX-1)	N/A
IMO A.652(16)8.2	N/A
ASTM E 84: CLASS I or A RATING	N/A