

Persuasion

DESCRIPTION

WEIGHT (LINEAR YARD)	28.0 oz
WIDTH	54"
THICKNESS	1.00 mm
GAUGE	0.040
SURFACE COMPOSITION	100 % PVC
SUBSTRATE COMPOSITION	100% Polyester Knit

GENERAL TREATMENTS

COLORFASTNESS TO LIGHT	650 Hours, AATCC Test Method 16- 2004, Option 3
COLD CRACK	-20° F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass, CFFA-120 / ASTM G21-09
ANTI-BACTERIAL	Pass, CFFA-300 / AATCC 147-2011
ANTI-MICROBIAL	Pass, CFFA-120 / ASTM G21-09
STAIN RESISTANT	Yes, with Resilience™
BLEACH RESISTANT	Yes, 10% Bleach Solution
SULFIDE STAIN RESISTANT	Yes

PHYSICAL PROPERTIES

ABRASION	250,000 Double Rubs, CFFA-1A / Method ASTM D 4157-10 ACT STANDARD COTTONDUCK
BREAKING STRENGTH	95 Warp, 60 Fill, CFFA-17 / ASTM D751-06 (2011)
BLOCKING	2 Rating, CFFA-4 / FTMS 191A TM5872
COATING ADHESION	6.26 Warp, 5.58 Fill, CFFA-3 / ASTM D751-06 (2011)
FLEX RESISTANCE	25,000 Cycles, CFFA-10 /ASTM 2097-03(2010)
SEAM STRENGTH: TACK TEAR	45 Warp 45 Fill, CFFA-14 / ASTM D751-06 (2011)
TEAR STRENGTH: TONGUE TEAR	5.1 Warp 6.9 Fill ,CFFA-16b / ASTM D751-06(2011)

FLAME RETARDANCY STANDARDS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS 1	Pass
MVSS 302	Pass
IMO 2010 FTP Code, Part 8	Pass

REDUCED ENVIRONMENTAL IMPACT

- PHthalate FREE (INCLUDES ALL PHthalATES LISTED IN CAL PROP 65 & CPSIA)
- LEAD FREE
- BPA FREE/TRIS FREE/FORMALDEHYDE FREE
- DOES NOT CONTAIN CONFLICT MINERALS



*ACT® Registered Certification Marks