

## Piano

### GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	25.0 oz
WIDTH	54"
THICKNESS	0.90 mm
GAUGE	36.000
EMBOSS	Smooth
SURFACE COMPOSITION	100% Polyurethane
SUBSTRATE COMPOSITION	100% Polyester
SUBSTRATE WEIGHT	6.5 oz

### GENERAL TREATMENTS

HYDROLYSIS RESISTANCE	7 yrs, ISO 1419:1995 (Jungle Test)
UV RESISTANCE	200 Hours, CFFA-2/ ASTM G26-96 Method C
COLD CRACK	-20 F, CFFA-6 Federal Standard No. 191A-Method 5874
BLEACH RESISTANT	Yes, Diluted 1:10

### PHYSICAL STRENGTH PROPERTIES

ABRASION	500,000 Cycles, CFFA-1A/ Method ASTM D 4157-92
ADHESION	7.5 Warp, 6.9 Fill, CFFA-16/ ASTM D5733-95
TEAR STRENGTH	170 Warp, 90 Fill, CFFA-17/ ASTM D751-98
SEAM STRENGTH	50.3 Warp, 49.4 Fill, CFFA-14/ Method ASTM D751-98
BLOCKING RESISTANCE	1 Rating, CFFA-4/ FTMS 191A-TM5872
CROCKING	5 Dry, 5 Wet, AATCC-Method 8-2001
FLEX TESTING OF FINISH	25,000 Warp, 25,000 Fill, CFFA-10/ASTM D2097-03(2005)

### FLAME RETARDANCY

CALIFORNIA TECHNICAL BULLETIN 117	Pass
UFAC CLASS I	Pass
BIFMA CS-191-53, SECTION 3	Pass
BIFMA UPHOLSTERY, SECTION 4	Pass
NFPA 260	Pass
BOSTON FIRE CODE (BFD IX-1)	N/A
IMO A.652(16)8.2	Pass
IMO A.652(16)8.3	Pass
ASTM E 84	Pass