

Piano

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	25.0 oz
WIDTH	54"
THICKNESS	0.90 mm
GAUGE	36.00
EMBOSS	Smooth
SURFACE COMPOSITION	100% Polyurethane
SUBSTRATE COMPOSITION	100% Polyester Knit

GENERAL TREATMENTS

HYDROLYSIS RESISTANCE	7 weeks, ISO 1419:1995 (Jungle Test)
COLORFASTNESS TO LIGHT	200 Hours, CFFA-2/ AATCC16-3
COLD CRACK	-20 F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass, CFFA-120/ ASTM G21-96
ANTI-BACTERIAL/ANTI-MICROBIAL	Pass, CFFA-300/ AATCC* Test Method 147-1998
STAIN RESISTANT	Yes, with Cleangene™ Technology
BLEACH RESISTANT	Yes, 1:10 Dilution

PHYSICAL STRENGTH PROPERTIES

ABRASION	500,000 Double Rubs, CFFA-1A/ Method ASTM D 4157-92
COATING ADHESION	7.5 Warp, 6.9 Fill, CFFA 3/ ASTM D751-06
TEAR STRENGTH: TONGUE TEAR	170 Warp, 90 Fill, CFFA-16B/ ASTM D2261-96
BREAKING STRENGTH	89 Warp, 159 Fill, CFFA-17/ Method ASTM D751-06
SEAM STRENGTH: TACK TEAR	50.3 Warp, 49.4 Fill, CFFA-14/ Method ASTM D751-06
CROCKING	5 Dry, 5 Wet, AATCC-Method 8-2001
FLEX RESISTANCE	25,000 Warp, 25,000 Fill, CFFA-10/ASTM D2097-03(2005)

FLAME RETARDANCY

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass
IMO 2010 FTP CODE, PART 8 (3.1)	Pass
ASTM E-84 (ADHERED & UNADHERED): CLASS 1 OR A	Pass

REDUCED ENVIRONMENTAL IMPACT

- PHthalate FREE (INCLUDES ALL PHthalATES LISTED IN CAL PROP 65 & CPSIA)
- LEAD FREE
- BPA FREE/TRIS FREE/FORMALDEHYDE FREE
- DOES NOT CONTAIN CONFLICT MINERALS



*ACT® Registered Certification Marks