

## Promo Automotive

### GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	28 oz
WIDTH	54"
THICKNESS	0.90 mm
GAUGE	0.036
EMBOSS	Various
SURFACE COMPOSITION	PVC
SUBSTRATE COMPOSITION	Polyester
SUBSTRATE WEIGHT	3.5 oz

### GENERAL TREATMENTS

UV RESISTANCE	200 Hours, CFFA-2/ ASTM G26-96 Method C
COLD CRACK	-10 F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	N/A, CFFA-120 / ASTM G21-96
ANTI-BACTERIAL	N/A, CFFA-300 / AATCC* Test Method 147-2004
ANTI-MICROBIAL	N/A, CFFA-300 / AATCC* Test Method 147-2004
RESILIENCE SR	N/A
BLEACH RESISTANT	N/A

### PHYSICAL STRENGTH PROPERTIES

ABRASION	50,000 Cycles, CFFA-1A/ Method ASTM D 4157-92
ADHESION	N/A Warp, N/A Fill, CFFA 3/ ASTM D751-98
TEAR STRENGTH	14.2 Warp, 25.4 Fill, CFFA-16/ ASTM D5733-95
TENSILE STRENGTH & ELONGATION	70 Warp, 83 Fill, CFFA-17/ ASTM D751-98
SEAM STRENGTH	N/A Warp, N/A Fill, CFFA-14/ Method ASTM D751-98
STRETCH AND SET	N/A Warp, N/A Fill, CFFA-15/ SAE Method J-855

### FLAME RETARDANCY

CALIFORNIA TECHNICAL BULLETIN 117	Pass
UFAC CLASS I	Pass
BIFMA CS-191-53, SECTION 3	Pass
BIFMA UPHOLSTERY, SECTION 4	Pass
NFPA 260	N/A
MVSS 302	N/A
BOSTON FIRE CODE (BFD IX-1)	N/A
IMO A.652(16)8.2	N/A
ASTM E 84: CLASS I OR A RATING	N/A