

Promo Automotive

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	28 oz
WIDTH	54"
THICKNESS	0.90 mm
GAUGE	0.036
EMBOSS	Various
SURFACE COMPOSITION	PVC
SUBSTRATE COMPOSITION	Polyester
SUBSTRATE WEIGHT	3.5 oz

GENERAL TREATMENTS

UV RESISTANCE	200 Hours, CFFA-2/ ASTM G26-96 Method C
COLD CRACK	-10 F, CFFA-6 Federal Standard No. 191A-Method 5874

PHYSICAL STRENGTH PROPERTIES

ABRASION	50,000 Cycles, CFFA-1A/ Method ASTM D 4157-92
TEAR STRENGTH: TONGUE TEAR	14.2 Warp, 25.4 Fill, CFFA-16/ ASTM D5733-95
BREAKING STRENGTH	70 Warp, 83 Fill, CFFA-17/ ASTM D751-98

FLAME RETARDANCY STANDARDS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
BIFMA CS-191-53, SECTION 3	Pass
BIFMA UPHOLSTERY, SECTION 4	Pass