

Promo Marine

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	28 oz
WIDTH	54"
THICKNESS	0.90 mm
GAUGE	0.036
SURFACE COMPOSITION	PVC
SUBSTRATE COMPOSITION	Polyester
SUBSTRATE WEIGHT	3.5 oz

GENERAL TREATMENTS

UV RESISTANCE	500 Hours, CFFA-2/ ASTM G26-96 Method C
COLD CRACK	-10 F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Yes, CFFA-120 / ASTM G21-96

PHYSICAL PROPERTIES

ABRASION	50,000 Cycles, CFFA-1A/ Method ASTM D 4157-92
TEAR STRENGTH: TONGUE TEAR	21.4 Warp, 21.65 Fill, FTM 5136
BREAKING STRENGTH	83.3 Warp, 81.1 Fill, FTM 5100.1

FLAME TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
BIFMA CS-191-53, SECTION 3	Pass
BIFMA UPHOLSTERY, SECTION 4	Pass