

Salinger

DESCRIPTION

WEIGHT (LINEAR YARD)	20.0 oz
WIDTH	54"
THICKNESS	1.00 mm
GAUGE	0.04
SURFACE COMPOSITION	100 % Polyurethane (Polycarbonate)
SUBSTRATE COMPOSITION	100 % Polyester Knit

GENERAL TREATMENTS

HYDROLYSIS RESISTANCE	7 weeks, ISO1419:1995 (Jungle Test)
COLORFASTNESS TO LIGHT	200 Hours CFFA-2 / AATCC 16-Option 3
COLD CRACK	-20 ° F, CFFA-6a Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass, CFFA-120 / ASTM G21-96)
ANTI-BACTERIAL / ANTI-MICROBIAL	Pass, CFFA-300 / AATCC* Test Method 147-2004
STAIN RESISTANT	Yes, with Writer's Block™
BLEACH RESISTANT	Yes, 20% Dilution

PHYSICAL PROPERTIES

ABRASION	250,000+ Double Rubs, CFFA-1A / Method ASTM D 4157-92
COATING ADHESION	11.4 Warp, 10.8 Fill, CFFA 3 / ASTM D751-06
TEAR STRENGTH: TONGUE TEAR	5.1 Warp, 2.9 Fill, CFFA-16b / ASTM D2261-96
BREAKING STRENGTH	144 Warp, 113 Fill, CFFA-17 / ASTM D751-06
SEAM STRENGTH: TACK TEAR	59.6 Warp, 44.4 Fill, CFFA-14 / Method ASTM D751-06
BLOCKING RESISTANCE	1 Rating, CFFA-4 / FTMS 191A-Method 5872
CROCKING	5 Dry, 5 Wet, AATCC-Method 8-2001

FLAME TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS 1	Pass
FMVSS 302	Pass
NFPA 260	Pass
IMO 2010 FTP Code, Part 8 (3.1)	Pass
ASTM E-84 (Unadhered): Class 1 or A	Pass

REDUCED ENVIRONMENTAL IMPACT

- 7P PHTHALATE FREE (INCLUDES ALL PHTHALATES LISTED IN CAL PROP 65 & CPSIA)
- LEAD FREE
- BPA FREE/TRIS FREE/FORMALDEHYDE FREE
- DOES NOT CONTAIN CONFLICT MINERALS



*ACT® Registered Certification Marks