

# NASSIMI

## PRODUCT SPECIFICATION SHEET

### San Remo

#### DESCRIPTION

WEIGHT (LINEAR YARD)	36.0 oz
WIDTH	54"
THICKNESS	1.10 mm
EMBOSS	SE-860
SURFACE COMPOSITION	100 % PVC
SUBSTRATE COMPOSITION	75 % Polyester/ 25% Cotton

#### GENERAL TREATMENTS

COLORFASTNESS TO LIGHT	200 Hours, AATCC Test Method 16-Option 3
COLD CRACK	-10 ° F, CFFA-6a Federal Standard No. 191A-Method 5874

#### PHYSICAL PROPERTIES

ABRASION	100,000 Double Rubs, CFFA-1A / Method ASTM D751-10 STANDARD COTTONDUCK
BREAKING STRENGTH	67 Warp, 78 Fill, CFFA-17 / ASTM D751-06(2011)
SEAM STRENGTH: TACK TEAR	67 Warp, 64 Fill, CFFA-14 / ASTM D751-06(2011)
TEAR STRENGTH: TONGUE TEAR	7.1 Warp, 6.3 Fill, CFFA-16b / ASTM D2261-96(2011)
COLORFASTNESS TO CROCKING	5 Wet, 5 Dry, CFFA-7/AATCC 8-2007
STRETCH AND SET	97.9 Wrap, 95.5 Fill, CFFA-15/ SAE J855 2009

#### FLAME TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS 1	Pass
MVSS 302	Pass
NFPA 260	Pass
IMO 2010 FTP CODE, PART 8	Pass
ASTM E-84 ( ADHERED ) : CLASS 1 OR A	Pass

#### REDUCED ENVIRONMENT IMPACT

21P PHTHALATE FREE ( INCLUDES ALL PHTHALATES LISTED IN CAL PROP 65 &CPSIA)
LEAD FREE
BPA FREE/ TRIS FREE/ FORMALDEHYDE FREE
DOES NOT CONTAIN CONFLICT MINERALS



\*ACT® Registered Certification Marks