

Savanna

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	28.0 oz
WIDTH	54"
THICKNESS	1.00 mm
GAUGE	0.040
SURFACE COMPOSITION	100 % PVC
SUBSTRATE COMPOSITION	100% Polyester
SUBSTRATE WEIGHT	4.0 oz

GENERAL TREATMENTS

UV RESISTANCE	200 Hours , AATCC Test Method 16-2004, Option 3
COLD CRACK	-20 °F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass, CFFA-120 /ASTMG21-96
ANTI-BACTERIAL / ANTI-MICROBIAL	Pass, CFFA-300/AATCC 141-2004
STAIN RESISTANT	Yes, with Resilience™
BLEACH RESISTANT	Yes, 1:10 Dilution
SULFIDE STAIN RESISTANCE	Yes

PHYSICAL STRENGTH PROPERTIES

ABRASION	300,000+ Double Rubs, CFFA-1A / Method ASTM D 4157-10 ACT STANDARD COTTONDUCK
COATING ADHESION	10.2 Warp, 7.62 Fill, CFFA-16 / ASTM D751-06
TEAR STRENGTH: TONGUE TEAR	7 Warp, 6.1 Fill, CFFA-16 / ASTM D5733-95
BREAKING STRENGTH	84 Warp, 67 Fill, CFFA-17 / ASTM D751-06
SEAM STRENGTH: TACK TEAR	44.4 Warp, 33.8 Fill, CFFA-14 / ASTM D751-06
BLOCKING RESISTANCE	2 Rating, CFFA-4 / FTMS 191A-TM5872
CROCKING	4.5 Dry, 4.5 Wet, CFFA-17 / ASTM D751-98
FLEX RESISTANCE	25,000 Warp, 25,000 Fill, CFFA-10 / ASTM D2097-03

FLAME RETARDANCY STANDARDS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
BIFMA CS-191-53, SECTION 3 & 4	Pass
MVSS 302	Pass
NFPA 260	Pass
IMO 2010 FTP CODE, PART 8	Pass
ASTM E-84 (ADHERED & UNADHERED): CLASS 1 OR A	Pass



*ACT® Registered Certification Marks