

# Seaquest

## GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	32.0 oz
WIDTH	54"
THICKNESS	1.00 mm
GAUGE	0.040
EMBOSS	Wallaby
SURFACE COMPOSITION	PVC
SUBSTRATE COMPOSITION	100% Polyester Knit
SUBSTRATE WEIGHT	3.75 oz

## GENERAL TREATMENTS

COLORFASTNESS TO LIGHT	1000 Hours , AATCC Test Method 16- 2004, Option 3
COLD CRACK	-10 °F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Yes,CFFA-120 / ASTM G21-09

## PHYSICAL STRENGTH PROPERTIES

ABRASION	175,000+ Double Rubs, CFFA-1A / Method ASTM D 4157-10 ACT STANDARD COTTONDUCK
TEAR STRENGTH	25.8 Warp, 27.7 Fill, CFFA-16 / ASTM D5733-95
BREAKING STRENGTH	89.2 Warp, 102.7 Fill, CFFA-17 / ASTM D751-98

## FLAME RETARDANCY STANDARDS

CALIFORNIA TECHNICAL BULLETIN 117, SECTION E	Pass
UFAC CLASS I	Pass
BIFMA CS-191-53, SECTION 3	Pass
MVSS 302	Pass
IMO A.652(16)8.2	Pass
IMO A.652(16)8.3	Pass