

Seaquest

DESCRIPTION

WEIGHT (LINEAR YARD)	32.0 oz
WIDTH	54"
THICKNESS	1.00 mm
GAUGE	0.040
EMBOSS	Wallaby
SURFACE COMPOSITION	PVC
SUBSTRATE COMPOSITION	100% Polyester Knit
SUBSTRATE WEIGHT	3.75 oz

GENERAL TREATMENTS

COLORFASTNESS TO LIGHT	1000 hours, AATCC Test Method 16-2004, Option 3
COLD CRACK	-20 F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass, CFFA-120 / ASTM G21-96

PHYSICAL STRENGTH PROPERTIES

ABRASION	175,000+ Double Rubs, (CFFA-1A / Method ASTM D 4157-10 ACT STANDARD COTTONDUCK)
TEAR STRENGTH: TONGUE TEAR	25.8 Warp, 27.7 Fill, (CFFA-16 / ASTM D5733-95)
BREAKING STRENGTH	89.2 Warp, 102.7 Fill, (CFFA-17 / ASTM D751-06)

FLAME RETARDANCY TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS 1	Pass
BIFMA CS-191-53, SECTION 3	Pass
MVSS 302	Pass
IMO 2010 FTP Code, Part 8	Pass



*ACT® Registered Certification Marks