

Seduction

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	32.0 oz
WIDTH	54"
THICKNESS	1.05 mm
SURFACE COMPOSITION	100% PVC
SUBSTRATE COMPOSITION	100% Brushed Polyester Knit

GENERAL TREATMENTS

UV RESISTANCE	650 Hours , AATCC Test Method 16- 2004, Option 3
COLD CRACK	-20 °F, CFFA-6 Federal Standard No. 191A-Method 5874
MILDEW RESISTANT	Pass,CFFA-120 / ASTM G21-96
ANTI-BACTERIAL	Pass,CFFA-300 / AATCC* Test Method 147-1998
ANTI-MICROBIAL	Pass,CFFA-120 / ASTM G21-96
STAIN RESISTANT	Yes, with Resilience ^{SR}
BLEACH RESISTANT	Yes, 10% Dilution

PHYSICAL STRENGTH PROPERTIES

ABRASION	500,000+ Double Rubs, CFFA-1A / Method ASTM D 4157-10 ACT STANDARD COTTONDUCK
TEAR STRENGTH: TONGUE TEAR	7.7 Warp, 6.8 Fill, CFFA-16 / ASTM D2261-07a
BREAKING STRENGTH	128 Warp, 93 Fill, CFFA-17 / ASTM D751-06
SEAM STRENGTH: TACK TEAR	51 Warp, 37.8 Fill, CFFA-14 / Method ASTM D751-06
CROCKING	5 Dry, 5 Wet, AATCC-Method 8-2007
FLEX TESTING OF FINISH	Warp, Fill, CFFA-10 /ASTM D2097-03(2005)
COATING ADHESION	4.3 Warp, 3.93 Fill, ASTM D751-06

FLAME RETARDANCY STANDARDS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
BIFMA CS-191-53, SECTION 3	Pass
MVSS 302	Pass
NFPA 260	Pass
IMO 2010 FTP CODE, PART 8	Pass
ASTM E-84 (ADHERED & UNADHERED): CLASS 1 OR A	Pass

