

NASSIMI

PRODUCT SPECIFICATION SHEET

Ultra

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	17.0 oz
WIDTH	54"
THICKNESS	0.85 mm
GAUGE	0.03
EMBOSS	DE-43
SURFACE COMPOSITION	100% Polyurethane
SUBSTRATE COMPOSITION	80% Rayon/20% Polyester

GENERAL TREATMENTS

HYDROLYSIS RESISTANCE	7 weeks, ISO1419:1995 (Jungle Test)
COLORFASTNESS TO LIGHT	200 Hours, CFFA-2 / AATCC 16-3
COLD CRACK	-20° F, CFFA-6a Federal Standard No. 191A-Method 5874)
BLEACH RESISTANT	Yes, 1:10 Dilution

PHYSICAL STRENGTH PROPERTIES

ABRASION	100,000 Double Rubs, CFFA-1A / Method ASTM D 4157-92
TEAR STRENGTH - TONGUE	22 Warp, 13.8 Fill, CFFA-16b / ASTM D2261-96
STRETCH AND SET	99.8 Warp, 98 Fill, CFFA 15/SAE J855
CROCKING	5 Dry, 5 Wet, AATCC-Method 8-2001

FLAME RETARDANCY

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
BIFMA CS-191-53, SECTION 3 & 4	Pass
FMVSS 302	Pass
NFPA 260	Pass
IMO 2010 FTP CODE, PART 8 (3.1)	Pass
ASTM E-84 (ADHERED/UNADHERED): CLASS 1 OR A	Pass



*ACT® Registered Certification Marks