

NASSIMI

PRODUCT SPECIFICATION SHEET

Verve II

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	16.5 oz
WIDTH	54"
THICKNESS	0.85 mm
SURFACE COMPOSITION	Polyurethane 100%
SUBSTRATE COMPOSITION	Polyester Knit 100%

GENERAL TREATMENTS

HYDROLYSIS RESISTANCE	5 weeks, ISO1419:1995 (Jungle Test)
COLORFASTNESS TO LIGHT	200 Hours, CFFA-2 / QUV CFFA2/Xenon-ARC
COLD CRACK	-20 °F, CFFA-6a Federal Standard No. 191A-Method 5874
BLEACH RESISTANT	Yes, 3:1 Dilution

PHYSICAL STRENGTH PROPERTIES

ABRASION	250,000+ DR, CFFA-1A / Method ASTM D 4157-92
TEAR STRENGTH: TONGUE TEAR	7.4 Warp, 12.7 Fill, CFFA 16 / ASTM D751-00
BREAKING STRENGTH	143 Warp, 105 Fill, CFFA-17 / ASTM D751-06
SEAM STRENGTH: TACK TEAR	55.9 Warp, 44.9 Fill, CFFA-14 / Method ASTM D751-06
COATING ADHESION	10.28 Warp, 9.13 Fill, CFFA-3/ASTM D751-06
STRETCH & SET	94.1 Warp, 92.01 Fill, CFFA-15 / SAE J855 2009
CROCKING	5 Dry, 5 Wet
FLEX RESISTANCE	25,000 Cycles

FLAME TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass
ASTM E-84 (ADHERED & UNADHERED): CLASS 1 OR A	Pass
IMO 2010 FTP CODE, PART 8	Pass
FMVSS 302	Pass

REDUCED ENVIRONMENTAL IMPACT

LEAD FREE TO COMPLY WITH CAL PROP 65
FREE OR ALL PHTHALATES LISTED IN CAL PROP 65
BPA FREE/TRIS FREE/FORMALDEHYDE FREE
DOES NOT CONTAIN CONFLICT MINERALS
DOES NOT CONTAIN ANY FLAME RETARDANT ADDITIVES
DOES NOT CONTAIN ANY ANTI- MICROBIAL/ANTI BACTERIAL ADDITIVES
CALIFORNIA 1350



*ACT® Registered Certification Marks