

VINTAGE

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	36.0 oz
WIDTH	54"
THICKNESS	1.10 mm
EMBOSS	Vintage
SURFACE COMPOSITION	100% PVC
SUBSTRATE COMPOSITION	75% Polyester/25% Cotton

GENERAL TREATMENTS

COLORFASTNESS TO LIGHT	300 Hours, AATCC Test Method 16- 2004, Option 3
COLD CRACK	-10° F, CFFA-6 Federal Standard No. 191A-Method 5874
SULFIDE STAIN RESISTANT	Yes

PHYSICAL STRENGTH PROPERTIES

ABRASION	50,000 Double Rubs , CFFA-1A / Method ASTM D 4157-10 ACT STANDARD COTTONDUCK
BREAKING STRENGTH	67 Warp, 83 Fill, CFFA-17 / ASTM D751-06 (2011)
SEAM STRENGTH: TACK TEAR	68 Warp, 65 Fill, CFFA-14 / ASTM D751-06 (2011)
TEAR STRENGTH: TONGUE TEAR	5.6 Warp, 6.2 Fill, CFFA-16b / ASTM D751-06(2011)
CROCKING	4 Wet, 4.5 Dry, CFFA-7/AATCC 8-2007
STRETCH AND SET	99.31 Warp, 98.8 Fill, CFFA-15/SAE J855 2009

FLAME TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
BIFMA CS-191-53, SECTION 3 & 4	Pass
MVSS 302	Pass
IMO 2010 FTP CODE, PART 8	Pass
NFPA 260	Pass
ASTM E-84 (ADHERED) : CLASS 1 OR A	Pass

REDUCED ENVIRONMENTAL IMPACT

21P PHTHALATE FREE (INCLUDES ALL PHTHALATES LISTED IN CAL PROP 65 & CPSIA)
 LEAD FREE
 BPA FREE/TRIS FREE/FORMALDEHYDE FREE
 DOES NOT CONTAIN CONFLICT MINERALS