

Wilde

DESCRIPTION

WEIGHT (LINEAR YARD)	20.0 oz
WIDTH	54"
THICKNESS	1.00 mm
GAUGE	0.04
SURFACE COMPOSITION	100% Polyurethane (Polycarbonate)
SUBSTRATE COMPOSITION	75 % Polyester /25% Cotton

GENERAL TREATMENTS

HYDROLYSIS RESISTANCE	7 weeks, ISO1419:1995 (Jungle Test)
COLORFASTNESS TO LIGHT	200 Hours, CFFA-2 / AATCC 16-Option 3
COLD CRACK	-20 °F, CFFA-6a Federal Standard No. 191A-Method 5874)
MILDEW RESISTANT	Pass, CFFA-120 / ASTM G21-96
ANTI-BACTERIAL / ANTI-MICROBIAL	Pass, CFFA-300 / AATCC* Test Method 147-1998)
STAIN RESISTANT	Yes, with Writer's Block™
BLEACH RESISTANT	Yes, 20% Dilution

PHYSICAL STRENGTH PROPERTIES

ABRASION	165,000 Double Rubs, CFFA-1A / Method ASTM D 4157-92
COATING ADHESION	10.05 Warp, 6.76 Fill, CFFA 3 / ASTM D751-98
TEAR STRENGTH: TONGUE TEAR	11.3 Warp, 9.6 Fill, CFFA-16b / ASTM D2261-96
BREAKING STRENGTH	128 Warp, 106 Fill, CFFA-17 / ASTM D751-10
SEAM STRENGTH: TACK TEAR	88.7 Warp, 92 Fill, CFFA-14 / Method ASTM D751-07
BLOCKING RESISTANCE	1 Rating, CFFA-4 / FTMS 191A-Method 5872
CROCKING	5 Dry, 5 Wet, AATCC-Method 8-2001

FLAME TREATMENTS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass	REDUCED ENVIRONMENTAL IMPACT Lead Free to Comply with CAL Prop 65 Free of all Phthalates listed in CAL Prop 65 BPA Free/TRIS Free/Formaldehyde Free Does not contain Conflict Minerals
UFAC CLASS 1	Pass	
FMVSS 302	Pass	
NFPA 260	Pass	
IMO 2010 FTP CODE, PART 8 (3.1)	Pass	
ASTM E-84 (UNADHERED) : CLASS 1 OR A	Pass	