

Suede

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	33oz
WIDTH	54"
THICKNESS	1.00 mm
GAUGE	0.040
EMBOSS	Special
SURFACE COMPOSITION	PVC/Rayon
SUBSTRATE COMPOSITION	Poly/Cotton

GENERAL TREATMENTS

UV RESISTANCE	40 Hours , CFFA-2/ ASTM G26-96 Method C
COLD CRACK	-10 °F, CFFA-6 Federal Standard No. 191A-Method 5874
STAIN RESISTANT	Yes, with Resilience ^{SR}

PHYSICAL STRENGTH PROPERTIES

ABRASION	30,000 Cycles, CFFA-1A/ Method ASTM D 4157-92
TEAR STRENGTH	16.2 Warp, 23.1 Fill, CFFA-16/ ASTM D5733-95
BREAKING STRENGTH	98 Warp, 81 Fill, CFFA-17/ ASTM D751-98

FLAME RETARDANCY STANDARDS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
BIFMA CS-191-53, SECTION 3	Pass
BIFMA UPHOLSTERY, SECTION 4	Pass
MVSS 302	Pass
NFPA 260	Pass
IMO 2010 FTP CODE, PART 8 (3.1)	Pass