

NASSIMI

PRODUCT SPECIFICATION SHEET

Parker

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)	20.0 oz
WIDTH	54"
THICKNESS	1.00 mm
SURFACE COMPOSITION	100% Polyurethane
SUBSTRATE COMPOSITION	100% Polyester

GENERAL TREATMENTS

HYDROLYSIS RESISTANCE	5 Weeks, ISO1419:1995 (Jungle Test)
COLORFASTNESS TO LIGHT	200 Hours, AATCC 16.3-2014, Option 3
COLD CRACK	-20° F, CFFA-6a-2010
STAIN RESISTANT	Yes
BLEACH RESISTANT	Yes, 10% Dilution

PHYSICAL STRENGTH PROPERTIES

ABRASION	100,000+ Double Rubs, ASTM D4157-13 ACT STANDARD COTTONDUCK
TEAR STRENGTH: TONGUE TEAR	6.3 Warp, 11.1 Fill, D2261-13
BREAKING STRENGTH	109 Warp, 127 Fill, ASTM D751-06
SEAM STRENGTH: TACK TEAR	59.9 Warp, 57.4 Fill, ASTM D751-06
CROCKING	5 Dry, 5 Wet, AATCC 8-2016
COATING ADHESION	8.8 Warp, 7.1 Fill, ASTM D751-06

FLAME RETARDANCY STANDARDS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass

REDUCED ENVIRONMENTAL IMPACT

NO ADDED FLAME RETARDANT CHEMICALS
NO ADDED ANTI-MICROBIAL/ANTI-BACTERIAL CHEMICALS
PVC FREE
PHTHALATE FREE
LEAD FREE
HEAVY METAL FREE
BPA FREE/TRIS FREE/FORMALDEHYDE FREE
99% OF ALL WATER AND RAW MATERIALS USED IN PRODUCTION ARE RECLAIMED AND RECYCLED
DOES NOT CONTAIN CONFLICT MINERALS
FREE OF ADDED FLAME RETARDANT CHEMICALS



*ACT® Registered Certification Marks