

This is an up-to-date spec sheet. This pattern never contained flame retardant, anti-bacterial, or anti-microbial additives.

Parker

GENERAL SPECIFICATIONS

SURFACE COMPOSITION	100% Polyurethane
SUBSTRATE COMPOSITION	100% Polyester
WEIGHT	20 oz per linear yard
WIDTH	54"
THICKNESS	1.00 mm

ADDED PERFORMANCE SPECIFICATIONS

HYDROLYSIS RESISTANCE	5 weeks	ISO 1419:1995 (Jungle Test)
STAIN RESISTANCE	Yes	
COLORFASTNESS TO LIGHT	200 Hours	AATCC 16.3-2014, Option 3
BLEACH RESISTANCE	Yes, 10% Dilution	
COLD CRACK	-20° F	CFFA-6a-2007
SULFIDE STAIN RESISTANCE	Yes	

PHYSICAL PERFORMANCE SPECIFICATIONS

ABRASION RESISTANCE	100,000+ Double Rubs*	ASTM D4157-13
BREAKING STRENGTH	109 Warp, 127 Fill	ASTM D751-06
COATING ADHESION	8.8 Warp, 7.1 Fill	ASTM D751-06
CROCKING RESISTANCE	5 Dry, 5 Wet	AATCC 8-2016
FLEX RESISTANCE	25,000+	ASTM D2097-03
TEAR STRENGTH: TONGUE TEAR	6.3 Warp, 7.0 Fill	ASTM D751-06
SEAM STRENGTH: TACK TEAR	58.7 Warp, 55.52 Fill	ASTM D751-06

**Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.*

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass
FMVSS 302	Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65
 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT
 NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS
 LEAD / HEAVY METAL FREE
 BPA FREE / TRIS FREE / FORMALDEHYDE FREE
 DOES NOT CONTAIN CONFLICT MINERALS



*ACT® Registered Certification Marks