

This spec sheet has been updated to reflect the removal of flame retardant, anti-bacterial, and anti-microbial

Beckett

GENERAL SPECIFICATIONS

SURFACE COMPOSITION

SUBSTRATE COMPOSITION WEIGHT

WIDTH

THICKNESS

100% Polyurethane (Polycarbonate)

100% Polyester

20.0 oz per linear yard

54"

1.00 mm

ADDED PERFORMANCE SPECIFICATIONS

HYDROLYSIS RESISTANCE

STAIN RESISTANCE

COLORFASTNESS TO LIGHT

BLEACH RESISTANCE

MILDEW RESISTANCE ANTI-BACTERIAL

COLD CRACK

SULFIDE STAIN RESISTANCE

7 weeks

Yes

200 Hours

Yes. 20% Dilution

Pass

Pass

-20° F

Yes

ISO 1419:1995 (Jungle Test)

AATCC 16.3-2014, Option 3

AATCC 107-13, Modified

ASTM G21-13

AATC 147-2011

additives

CFFA-6a-2007

PHYSICAL PERFORMANCE SPECIFICATIONS

ABRASION RESISTANCE BREAKING STRENGTH COATING ADHESION

CROCKING RESISTANCE

FLEX RESISTANCE

TEAR STRENGTH: TONGUE TEAR SEAM STRENGTH: TACK TEAR

150.000+ Double Rubs 144 Warp, 113 Fill 11.4 Warp, 10.8 Fill

5 Dry, 5 Wet 25.000+

4.4 Warp, 8.5 Fill 57.3 Warp, 42.9 Fill ASTM D4157-13 ASTM D751-06 ASTM D751-06

AATCC 8-2016

ASTM D2097-03 ASTM D751-06

ASTM D751-06

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13

UFAC CLASS I NFPA 260

Pass Pass

Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS LEAD / HEAVY METAL FREE BPA FREE / TRIS FREE / FORMALDEHYDE FREE DOES NOT CONTAIN CONFLICT MINERALS









Disclaimer: This product meets the Healthy Interior goals of the Safer Chemical Challenge according to the manufacturer Practice Greenhealth does not verify this information











