

This spec sheet has been updated to reflect the removal of flame retardant, anti-bacterial, and anti-microbial additives.

Wilde

GENERAL SPECIFICATIONS

SURFACE COMPOSITION	100% Polyurethane (Polycarbonate)
SUBSTRATE COMPOSITION	75% Polyester/25% Cotton
WEIGHT	20.0 oz per linear yard
WIDTH	54"
THICKNESS	1.00 mm

ADDED PERFORMANCE SPECIFICATIONS

HYDROLYSIS RESISTANCE	7 weeks	ISO 1419:1995 (Jungle Test)
STAIN RESISTANCE	Yes	
COLORFASTNESS TO LIGHT	200 Hours	AATCC 16.3-2014, Option 3
BLEACH RESISTANCE	Yes, 20% Dilution	AATCC 107-13, Modified
MILDEW RESISTANCE	Pass	ASTM G21-13
ANTI-BACTERIAL	Pass	AATC 147-2011
COLD CRACK	-20° F	CFFA-6a-2010
SULFIDE STAIN RESISTANCE	Yes	

PHYSICAL PERFORMANCE SPECIFICATIONS

ABRASION RESISTANCE	165,000+ Double Rubs	ASTM D4157-13
BREAKING STRENGTH	128 Warp, 106 Fill	ASTM D751-06
COATING ADHESION	4.8 Warp, 4.3 Fill	ASTM D751-06
CROCKING RESISTANCE	5 Dry, 5 Wet	AATCC 8-2016
FLEX RESISTANCE	25,000+	ASTM D2097-03
TEAR STRENGTH: TONGUE TEAR	11.3 Warp, 7.6 Fill	ASTM D751-06
SEAM STRENGTH: TACK TEAR	88.7 Warp, 87.9 Fill	ASTM D751-06

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65
 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT
 NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS
 LEAD / HEAVY METAL FREE
 BPA FREE / TRIS FREE / FORMALDEHYDE FREE
 DOES NOT CONTAIN CONFLICT MINERALS



Disclaimer: This product meets the Healthy Interior goals of the Safer Chemical Challenge according to the manufacturer Practice Greenhealth does not verify this information.



*ACT® Registered Certification Marks