

This spec sheet has been updated to reflect the removal of flame retardant, anti-bacterial, and anti-microbial additives.

Muse

GENERAL SPECIFICATIONS

| | |
|------------------------------|---------------------------|
| SURFACE COMPOSITION | 100% PVC (Phthalate Free) |
| SUBSTRATE COMPOSITION | 100% Polyester |
| WEIGHT | 32.0 oz per linear yard |
| WIDTH | 54" |
| THICKNESS | 1.15 mm |

ADDED PERFORMANCE SPECIFICATIONS

| | | |
|---------------------------------|-------------------|---------------------------|
| STAIN RESISTANCE | Yes | |
| COLORFASTNESS TO LIGHT | 500 Hours | AATCC 16.3-2004, Option 3 |
| BLEACH RESISTANCE | Yes, 20% Dilution | AATCC 107-13, Modified |
| COLD CRACK | -20° F | CFFA-6a-2007 |
| SULFIDE STAIN RESISTANCE | Yes | |

PHYSICAL PERFORMANCE SPECIFICATIONS

| | | |
|-----------------------------------|--------------------------|---------------|
| ABRASION RESISTANCE | 500,000+ Double Rubs | ASTM D4157-10 |
| BREAKING STRENGTH | 131 Warp, 95 Fill | ASTM D751-06 |
| COATING ADHESION | 8.9 Warp, Full Bond Fill | ASTM D751-06 |
| CROCKING RESISTANCE | 5 Dry, 5 Wet | AATCC 8-2007 |
| FLEX RESISTANCE | 25,000+ | ASTM D2097-03 |
| TEAR STRENGTH: TONGUE TEAR | 8.5 Warp, 6.5 Fill | ASTM D2261-07 |
| SEAM STRENGTH: TACK TEAR | 60 Warp, 40 Fill | ASTM D751-06 |

FLAME RETARDANCY SPECIFICATIONS

| | |
|--------------------------------------|------|
| CALIFORNIA TECHNICAL BULLETIN 117:13 | Pass |
| UFAC CLASS I | Pass |
| NFPA 260 | Pass |
| FMVSS 302 | Pass |

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65
 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT
 NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS
 PHTHALATE FREE
 LEAD / HEAVY METAL FREE
 BPA FREE / TRIS FREE / FORMALDEHYDE FREE
 DOES NOT CONTAIN CONFLICT MINERALS



*ACT® Registered Certification Marks