



SiO™

The medical performance grade silicone™

This is an up-to-date spec sheet. This pattern never contained flame retardant, anti-bacterial, or anti-microbial additives.

Envision

| | |
|------------------------------|-----------------------|
| SURFACE COMPOSITION | 100% SiO™ Silicone |
| SUBSTRATE COMPOSITION | 100% Polyester |
| WEIGHT | 28 oz per linear yard |
| WIDTH | 54" |
| THICKNESS | 1.10 mm |

ADDED PERFORMANCE SPECIFICATIONS

| | | |
|--------------------------------------|-------------------|---------------------------|
| STAIN RESISTANCE | Yes | |
| UV RESISTANCE | 1300 Hours | ASTM G154-06 |
| COLORFASTNESS TO LIGHT | 500 Hours | AATCC 16.3-2014, Option 3 |
| BLEACH RESISTANCE | Yes, 10% Dilution | |
| MILDEW RESISTANCE | Pass | ASTM G21-13 |
| ANTI-BACTERIAL | Pass | AATCC 147-11 |
| COLD CRACK | -20° F | CFFA-6a-2010 |
| DENIM DYE TRANSFER RESISTANCE | Yes | Ford BN 112-09 |
| SULFIDE STAIN RESISTANCE | Yes | |
| PINK STAIN RESISTANCE | Yes | ASTM E1428 |
| ANTI-STATIC | Pass | AATCC-76 |
| CYTOTOXICITY | Degree 0 | ISO 10993-5 |
| SKIN IRRITATION | No reaction | ISO 10993-10 |
| SALT SPRAY RESISTANCE | 1,000+ Hours | ASTM B117 |
| INK RESISTANCE | Yes | |
| ISOPROPYL ALCOHOL RESISTANCE | Yes, 70% Dilution | |

PHYSICAL PERFORMANCE SPECIFICATIONS

| | | |
|-----------------------------------|--------------------------------|---------------|
| ABRASION RESISTANCE | 225,000 Double Rubs* | ASTM D4157-13 |
| BREAKING STRENGTH | 250 Warp, 279 Fill | ASTM D751-00 |
| COATING ADHESION | Full Bond Warp, Full Bond Fill | ASTM D751-06 |
| CROCKING RESISTANCE | 5 Dry, 5 Wet | AATCC 8-2016 |
| FLEX RESISTANCE | 25,000+ | ASTM D2097-03 |
| TEAR STRENGTH: TONGUE TEAR | 10.7 Warp, 11.8 Fill | ASTM D751-06 |
| SEAM STRENGTH: TACK TEAR | 88.9 Warp, 97.84 Fill | ASTM D751-06 |

**Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.*

FLAME RETARDANCY SPECIFICATIONS

| | |
|--------------------------------------|------|
| CALIFORNIA TECHNICAL BULLETIN 117:13 | Pass |
| UFAC CLASS I | Pass |
| NFPA 260 | Pass |
| IMO 2010 FTP CODE, PT. 8 | Pass |
| ASTM E84 (ADHERED & UNADHERED) | Pass |
| BS 5852: 2006 Crib 5 | Pass |
| FMVSS 302 | Pass |

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65
 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT
 NO ADDED ANTI-BACTERIAL CHEMICALS
 PHTHALATE FREE
 LEAD / HEAVY METAL FREE
 BPA FREE / TRIS FREE / FORMALDEHYDE FREE
 DOES NOT CONTAIN CONFLICT MINERALS



Disclaimer: This product meets the Healthy Interior goals of the Safer Chemical Challenge according to the manufacturer Practice Greenhealth does not verify this information.



*ACT® Registered Certification Marks