

Aura

GENERAL SPECIFICATIONS

SURFACE COMPOSITION	100% Polyurethane
SUBSTRATE COMPOSITION	100% Polyester
WEIGHT	18 oz per linear yard
WIDTH	54"
THICKNESS	0.80 mm

ADDED PERFORMANCE SPECIFICATIONS

HYDROLYSIS RESISTANCE	7 weeks	ISO 1419:1995 (Jungle Test)
STAIN RESISTANCE	Yes	
COLORFASTNESS TO LIGHT	200 Hours	AATCC 16.3-2014, Option 3
BLEACH RESISTANCE	Yes, 10% Dilution	
MILDEW RESISTANCE	Pass	ASTM G-21 -96
ANTI-BACTERIAL	Pass	AATCC 147
COLD CRACK	-20° F	CFFA-6a-2007
SULFIDE STAIN RESISTANCE	Yes	

PHYSICAL PERFORMANCE SPECIFICATIONS

ABRASION RESISTANCE	500,000+ Double Rubs*	ASTM D4157-02
BREAKING STRENGTH	172.0 Warp, 103.0 Fill	ASTM D751-00
COATING ADHESION	10.0 Warp, 10.3 Fill	ASTM D751-00
CROCKING RESISTANCE	4.5 Dry, 4.5 Wet	AATCC 8-2001
FLEX RESISTANCE	25,000+	ASTM D2097-03
TEAR STRENGTH: TONGUE TEAR	10.3 Warp, 16.2 Fill	ASTM D2261-92
SEAM STRENGTH: TACK TEAR	63.4 Warp, 46.3 Fill	ASTM D751-00

*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass
BIFMA X5.7-1991 Section 4	Pass
IMO 2010 FTP Code, Part 8.2	Pass
ASTM E84 (ADHERED & UNADHERED)	Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65
LEAD / HEAVY METAL FREE
BPA FREE / TRIS FREE / FORMALDEHYDE FREE
DOES NOT CONTAIN CONFLICT MINERALS



*ACT® Registered Certification Marks