RESILIENCE

Þ

ASTM D751-06

The faux leather that builds luxury into performance

This spec sheet has been updated to reflect the removal of flame retardant and anti-bacterial additives.

Esprit

GENERAL SPECIFICATIONS SURFACE COMPOSITION SUBSTRATE COMPOSITION WEIGHT WIDTH THICKNESS	100% PVC 100% Polyester 30 oz per linear yard 54" 0.97 mm	
ADDED PERFORMANCE SPECIFICATIONS STAIN RESISTANCE COLORFASTNESS TO UV BLEACH RESISTANCE MILDEW RESISTANT COLD CRACK SULFIDE STAIN RESISTANCE	Yes 1,000 Hours Yes, 10% Dilution Pass -20° F Yes	ASTM G154-16 ASTM G21-13 CFFA-6a-2007
PHYSICAL PERFORMANCE SPECIFICATIONS ABRASION RESISTANCE BREAKING STRENGTH CROCKING RESISTANCE FLEX RESISTANCE TEAR STRENGTH: TONGUE TEAR	250,000+ Double Rubs 95 Warp, 73 Fill 5 Dry, 5 Wet 25,000+ 11.9 Warp, 15.4 Fill	ASTM D4157-13 ASTM D751-06 AATCC 8-2007 ASTM D2097-03 ASTM D751-06

67 Warp, 43 Fill

*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

FLAME RETARDANCY SPECIFICATIONS

SEAM STRENGTH: TACK TEAR

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT NO ADDED ANTI-BACTERIAL CHEMICALS 7P PHTHALATE FREE LEAD / HEAVY METAL FREE BPA FREE / TRIS FREE / FORMALDEHYDE FREE DOES NOT CONTAIN CONFLICT MINERALS





^{*}ACT® Registered Certification Marks