RESILIENCE

P

The faux leather that builds luxury into performance

This is an up-to-date spec sheet. This pattern never contained flame retardant, anti-bacterial, or anti-microbial additives.

Foundation

| GENERAL SPECIFICATIONS SURFACE COMPOSITION SUBSTRATE COMPOSITION WEIGHT WIDTH THICKNESS | 100% PVC 100% Polyester 30 oz per linear yard 54" 1.00 mm | |
|--|---|---------------------------|
| ADDED PERFORMANCE SPECIFICATIONS | | |
| STAIN RESISTANCE COLORFASTNESS TO LIGHT | Yes 300 Hours | AATCC 16 7-2014 Option 7 |
| BLEACH RESISTANCE | Yes, 10% Dilution | AATCC 16.3-2014, Option 3 |
| COLD CRACK | -20° F | CFFA-6a-2007 |
| SULFIDE STAIN RESISTANCE | Yes | |
| PHYSICAL PERFORMANCE SPECIFICATIONS | | |
| ABRASION RESISTANCE | 100,000+ Double Rubs* | ASTM D4157-13 |
| BREAKING STRENGTH | 101 Warp, 93 Fill | ASTM D751-06 |
| COATING ADHESION | 10.2 Warp, 11.5 Fill | ASTM D751-06 |
| CROCKING RESISTANCE | 5 Dry, 5 Wet | AATCC 8-2013 |
| FLEX RESISTANCE | 25,000+ | ASTM D2097-03 |
| TEAR STRENGTH: TONGUE TEAR | 6.8 Warp, 8.0 Fill | ASTM D751-06 |
| SEAM STRENGTH: TACK TEAR | 50 Warp, 50 Fill | ASTM D751-06 |

*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

FLAME RETARDANCY SPECIFICATIONS

| CALIFORNIA TECHNICAL BULLETIN 117:13 | Pass |
|--------------------------------------|------|
| UFAC CLASS I | Pass |
| NFPA 260 | Pass |
| FMVSS 302 | Pass |

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS 7P PHTHALATE FREE LEAD / HEAVY METAL FREE BPA FREE / TRIS FREE / FORMALDEHYDE FREE DOES NOT CONTAIN CONFLICT MINERALS





*ACT® Registered Certification Marks