

Fulton

GENERAL SPECIFICATIONS

| | | |
|---|--|-------------------------------------|
| WEIGHT (LINEAR YARD) | 17/18 oz per linear yard | |
| WIDTH | 54" | |
| COMPOSITION | 100% Polyester | |
| <input type="checkbox"/> PIECE DYED | <input checked="" type="checkbox"/> YARN DYED | <input type="checkbox"/> FIBER DYED |
| <input checked="" type="checkbox"/> DOBBY | <input type="checkbox"/> JACQUARD | <input type="checkbox"/> PILE |
| YARN PER INCH | 47.5 EPI, 36.6 PPI | |
| YARN SIZE | T150D+T1600D Warp, T8S+T1600D Fill | |
| BACKING | SBR | |
| STAIN RESISTANCE | C6 | |
| CLEANING CODE | SW, Spot clean with upholstery shampoo, foam from a mild detergent, or a mild dry cleaning solvent. Do not saturate with liquid. Pile fabrics may require brushing to restore appearance. Cushion cover should not be removed and dry cleaned. | |

t

PHYSICAL PERFORMANCE SPECIFICATIONS

| | | |
|----------------------------|-----------------------|---------------------------|
| ABRASION RESISTANCE | 100,000+ Double Rubs* | ASTM D4157-13 |
| BREAKING STRENGTH | 323 Warp, 299 Fill | ASTM D5034-09 |
| BRUSH PILL | Class 3.5 | ASTM D3511 |
| CROCKING RESISTANCE | 4.5 Dry, 4.5 Wet | AATCC 8-2013 |
| COLORFASTNESS TO LIGHT | Class 5 | AATCC 16.3-2014, Option 3 |
| SEAM SLIPPAGE | 39.7 Warp, 33.7 Fill | ASTM D4034-92 |
| TEAR STRENGTH: TONGUE TEAR | 73 Warp, 63 Fill | ASTM D2261-13 |

**Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.*

FLAME RETARDANCY SPECIFICATIONS

| | |
|--------------------------------------|------|
| CALIFORNIA TECHNICAL BULLETIN 117:13 | Pass |
| UFAC CLASS I | Pass |
| NFPA 260 | Pass |

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65
 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT
 NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS
 LEAD / HEAVY METAL FREE
 BPA FREE / TRIS FREE / FORMALDEHYDE FREE
 DOES NOT CONTAIN CONFLICT MINERALS



*ACT® Registered Certification Marks