Harrison Wool

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD) 15/16 oz per linear yard

WIDTH

COMPOSITION 70% Wool / 20% Polyester / 5% Acrylic / 5% Nylon

□ PIECE DYED □ YARN DYED ■ FIBER DYED

■ DOBBY □ JACQUARD □ PILE

YARN PER INCH 38.1 EPI, 34.5 PPI

YARN SIZE MN 8.3 Warp, MN 8.3 Fill CLEANING CODE SW, Spot clean with uphols:

SW, Spot clean with upholstery shampoo, foam from a mild detergent, or a mild dry cleaning solvent. Do not saturate with liquid. Pile fabrics may require brushing to restore appearance. Cushion cover should not

be removed and dry cleaned.

PHYSICAL PERFORMANCE SPECIFICATIONS

ABRASION RESISTANCE 75,000+ Double Rubs* ASTM D4966-12
BREAKING STRENGTH 108.3 Warp, 57.4 Fill ASTM D5034-09
BRUSH PILL Class 3 ASTM D3511
CROCKING RESISTANCE 5 Dry, 5 Wet AATCC 8-2013

COLORFASTNESS TO LIGHT Class 5 AATCC 16.3-2014, Option 3

SEAM SLIPPAGE86.9 Warp, 56.0 FillASTM D4034-92TEAR STRENGTH: TONGUE TEAR11.8 Warp, 7.0 FillASTM D2261-13

*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13 Pass
UFAC CLASS I Pass
NFPA 260 Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65
NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT
NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS
LEAD / HEAVY METAL FREE
BPA FREE / TRIS FREE / FORMALDEHYDE FREE
DOES NOT CONTAIN CONFLICT MINERALS





*ACT® Registered Certification Mark