RESILIENCE

The faux leather that builds luxury into performance

Ð

This spec sheet has been updated to reflect the removal of flame retardant, anti-bacterial, and anti-microbial additives.

Kimono

GENERAL SPECIFICATIONS SURFACE COMPOSITION SUBSTRATE COMPOSITION WEIGHT WIDTH THICKNESS	100% PVC (Phthalate Free) 100% Polyester 30 oz per linear yard 54" 1.10 mm	
ADDED PERFORMANCE SPECIFICATIONS STAIN RESISTANCE COLORFASTNESS TO LIGHT BLEACH RESISTANCE COLD CRACK SULFIDE STAIN RESISTANCE	Yes 500 Hours Yes, 10% Dilution -20° F Yes	AATCC 16.3-2014, Option 3 CFFA-6a-2007
PHYSICAL PERFORMANCE SPECIFICATIONS ABRASION RESISTANCE BREAKING STRENGTH COATING ADHESION CROCKING RESISTANCE FLEX RESISTANCE TEAR STRENGTH: TONGUE TEAR SEAM STRENGTH: TACK TEAR	250,000+ Double Rubs* 121 Warp, 125 Fill 4.3 Warp, 4.6 Fill 5 Dry, 5 Wet 25,000+ 9.8 Warp, 11.7 Fill 44.8 Warp, 53.7 Fill	ASTM D4157-13; ASTM D751-06 ASTM D751-06 AATCC 8-2013 ASTM D2097-03 ASTM D751-06 ASTM D751-06

*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass
FMVSS 302	Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS PHTHALATE FREE LEAD / HEAVY METAL FREE BPA FREE / TRIS FREE / FORMALDEHYDE FREE DOES NOT CONTAIN CONFLICT MINERALS





*ACT® Registered Certification Marks